



POLI-FLEX PREMIUM

Product Information

POLI-FLEX PREMIUM is an ecologically proven polyurethane film with matt, reflection free surface, in accordance with Oeko-Tex Standard 100.

POLI-FLEX PREMIUM is suitable to transfer onto textiles like cotton, mixtures of polyester/cotton and polyester/acrylic. POLI-FLEX can be used for lettering on T-shirts, sport & leisure wear, sport bags and promotional articles.

POLI-FLEX PREMIUM can be cut with all current plotters. We recommend using a standard 45° knife. After weeding the cut flex film is transferred by heat press. The polyester liner should be removed warm, except for the neon colours (POLI-FLEX 440 – 443) and POLI-FLEX 403 Light Blue the liner should be removed after cooling down. Afterwards we recommend pressing the material for another 2 sec. with the same parameters. Nylon and textiles with hydrophobic impregnation are not suitable for heat transfer. In this case we recommend using POLI-FLEX NYLON.

The soft, elastic carrier film offers a comfortable textile touch and convinces due to high wearing comfort. POLI-FLEX PREMIUM excels due to an excellent opacity. POLI-FLEX PREMIUM with a self-adhesive polyester liner enables a reposition. The raw materials are ecologically inert, do not contain PVC, plasticizers or heavy metals (in accordance with Oeko-Tex Standard 100).

Guarantee for a secure and long-lasting bond of POLI-FLEX PREMIUM is only given when following the specified temperature and pressure conditions.

With the exception of 403 Light Blue, 420 Gold Metallic, 430 Silver Metallic and the Neon colours (440 – 443), the POLI-FLEX PREMIUM series can be pressed on top of each other.

Polyester textiles

Polyester textiles (e. g. football shirts, Softshell jackets) are coloured with special colouring. During the thermal transfer the colour particles are activated and could seep through the Flexmaterial. Therefore we recommend using POLI-FLEX BLOCKOUT instead of POLI-FLEX PREMIUM. The colours of the POLI-FLEX PREMIUM marked with a * have an excellent sublimation resistance even though they do not possess an extra blackout coating.

Technical Data

Carrier:	PET-film
Adhesive:	Polyurethane-hotmelt
Thickness [mm]:	0.10 +/- 5 %

Transfer Conditions

Temperature:	155° - 165° C
Pressure:	3.5 bar [medium pressure]
Time:	17 – 20 sec.

Wash Resistance

Wash resistance:	60° C Suitable for dry-cleaning. Wash textile inside out.
-------------------------	---

Standard Dimensions

500 mm x 25 m
1,000 mm x 25 m
1,524 mm x 25 m

We recommend evaluation on test material.

Due to the various influences which occur from production and transfer of plotter letterings, consistency of the carrier materials and also washing and cleaning conditions, product liability of course can only cover the unprocessed material.

26/06/2009



The following technical details are issued to the best of our knowledge, however, without any responsibility for results due to several different kinds of material and application processes. Therefore, we highly recommend that before every usage a test should be conducted on the original material.